

KUNSTSTOFF- UND FARBEN-GESELLSCHAFT mbH

An der Flurscheide 7 D-64584 Biebesheim
Tel. +49 (0) 6258-8006-0 Fax +49 (0) 6258-8006-70
E-Mail: info@kfg-biebesheim.de Internet: www.kfg-biebesheim.de



Technical Data Sheet

CarbAcrylit Siegelharz

Application	Glueing and sealing of orthopedic form parts
Chemical Basis	Methylmethacrylate resin
Appearance	viscous, lightly bluish resin
Curing	1-2% Dibenzoyl Peroxide 50 %
Pot Life Time/Curing Time(23°C)	approx. 10 min/15-20 min
Viscosity (Efflux Time)	115± 5 s (23°C, 4 mm cup, DIN 53211)
Barcol Hardness *	55
Cleaning of Tools	with acetone or methylmethacrylate
Storage	up to 6 months when stored dry and not > 35°C Keep containers tightly closed.

Our application technique consulting is not binding. The responsibility for the application resp. the processing of our products is in buyers hand, including property rights of third parties/patent rights. Technical data referring to our products are guide values.
(updated July 2014)

* measured with Barcol-Impressor GYZJ 934-1