

KUNSTSTOFF- UND FARBEN-GESELLSCHAFT mbH

An der Flurscheide 7 D-64584 Biebesheim
Tel. +49 (0) 6258-8006-0 Fax +49 (0) 6258-8006-70
E-Mail: info@kfg-biebesheim.de Internet: www.kfg-biebesheim.de



Technical Data Sheet

Härterpulver HP 10 W

Chemical basis:	Acryl powder with plastic fibres and dibenzoyl peroxide
Applications:	Repair mass for concrete and asphalt
Delivery Form:	Bright grey powder
Mixture ratio:	82 % HP10W : 18 % MO20
Bulk weight at 20 °C:	800 ± 10 % kg/m ³
Peroxide content:	ca. 3 % dibenzoyl peroxide (powder 50%)
Processing:	Mix in HP 10 W into MO 20 two minutes by a trowel, apply and press slightly. Traversable at 10°C after 30 min., at 20°C after 20 min.
Slip resistance	56 SRT
Tensile bond strength	2,0 N/mm ² (on asphalt)
Bending elongation	9-10 N/mm ² (at 3,5 %)
E-Modulus	480 N/mm ²
Packaging:	bags of 20 Kg or Big Bags
Storage stability:	6 months
Storage:	cool and dry

Our application-specific recommendation is non-committal. The responsibility for the application and the processing of our products lies at the buyer, also in respect of eventual protective rights of third parties. Technical data of our products are indications (updated February 2017).