

KUNSTSTOFF- UND FARBEN-GESELLSCHAFT mbH



An der Flurscheide 7 D-64584 Biebesheim
Tel. +49 (0) 6258-8006-0 Fax +49 (0) 6258-8006-70
E-Mail: info@kfg-biebesheim.de Internet: www.kfg-biebesheim.de

Technical Data Sheet

Pulverized Acrylic Glass XP 85 P

Chemical Basis	Polymethylmethacrylate
Average Molecular Weight	ca. 100,000 g/mol
Appearance	powder, colourless
Maximum Particle Size	<0,6 mm
Powder Density	600 - 700 g/l
Physiological Risks	not known
Density	1,1 g/cm ³
Decomposition Temperature	above 350°C
Acid Value	< 1 mg KOH
Solution time	100 min, [20% in MMA, at 40°C]
Viscosity	700 ± 50 cP; [27,3% in MMA]
Package	20 kg PE-bags or big bags
Application	acrylic solid surface
Storage	keep dry

Our application technique consulting is not binding. The responsibility for the application resp. the processing of our products is in buyers hand, including property rights of third parties/patent rights. Technical data referring to our products are guide values.
(updated December 2013)