

# KUNSTSTOFF- UND FARBEN-GESELLSCHAFT mbH



An der Flurscheide 7 D-64584 Biebesheim  
Tel. +49 (0) 6258-8006-0 Fax +49 (0) 6258-8006-70  
E-Mail: [info@kfg-biebesheim.de](mailto:info@kfg-biebesheim.de) Internet: [www.kfg-biebesheim.de](http://www.kfg-biebesheim.de)

## Technical Data Sheet

### Acrylic Beads G 100

<b>Chemical Basis</b>	Polymethylacrylate (PMMA)
<b>Available Particel Sizes</b>	0,00 - 0,1 mm 0,00 – 0,30 mm 0,20 – 0,60 mm 0,30 – 0,90 mm 0,90 – 1,30 mm
<b>Powder Density</b>	600 - 700 g/L
<b>Density</b>	1,1 g/cm <sup>3</sup>
<b>Vicat Softening Temperature</b>	90°C +/-5°C
<b>Decomposition</b>	above 350°C
<b>Physiological Risks</b>	not known
<b>Package</b>	25 kg PE-bags stretched on pallets or in octabins
<b>Application</b>	vibratory finishing, media blast, separating agent
<b>Storage</b>	keep dry

Our application technique consulting is not binding. The responsibility for the application resp. the processing of our products is in buyers hand, including property rights of third parties/patent rights. Technical data referring to our products are guide values.  
(updated April 2020 )