

KUNSTSTOFF- UND FARBEN-GESELLSCHAFT mbH

An der Flurscheide 7 D-64584 Biebesheim
Tel. +49 (0) 6258-8006-0 Fax +49 (0) 6258-8006-70
E-Mail: info@kfg-biebesheim.de Internet: www.kfg-biebesheim.de



Technical Data Sheet

MMA-Harz B 18

Chemical Basis	Resin from methylmethacrylate with polybutylmethacrylat
Appearance	bluish, low-viscose , slightly turbid liquid
Density	1 g/cm ³ (20°C)
Flashpoint	+ 10°C (MMA, DIN 51755)
Odour	ester-like
Viscosity after stirring	170 +/- 20 mPa s (23°C, Brookfield, Spindle 62, 100 rpm)
Efflux Time:	45 ± 3 s (23°C, 4mm cup, DIN 53211)
Handling	breathing protection in case of insufficient ventilation
Curing	2 % Dibenzoyl Peroxide 50%
Curing Time	25 - 30 min at 23°C
Pot Life	10-15 min at 23°C
Cleaning of Tools	acetone, methylmethacrylate
Application	binder for floor coatings
Storage	up to 6 months when stored dry and cool

Our application technique consulting is not binding. The responsibility for the application resp. the processing of our products is in buyers hand, including property rights of third parties/patent rights. Technical data referring to our products are guide values.
(updated December 2013)