

# KUNSTSTOFF- UND FARBEN-GESELLSCHAFT mbH

An der Flurscheide 7 D-64584 Biebesheim  
Tel. +49 (0) 6258-8006-0 Fax +49 (0) 6258-8006-70  
E-Mail: [info@kfg-biebesheim.de](mailto:info@kfg-biebesheim.de) Internet: [www.kfg-biebesheim.de](http://www.kfg-biebesheim.de)



## Technical Data Sheet

### MMA-Harz B 51

<b>Chemical Basis</b>	methylmethacrylate resin with polybutylmethacrylate
<b>Appearance</b>	bluish, low-viscose , slightly turbid liquid
<b>Flashpoint</b>	+ 10°C (MMA, DIN 51755)
<b>Odour</b>	ester-like
<b>Viscosity</b>	85+/- 20 mPa s ( 23°C Brookfield Spindle 62, 100 rpm)
<b>Efflux Time:</b>	27 ± 3 s (23°C, 4 mm cup, DIN 53211)
<b>Handling</b>	Breathing protection in case of insufficient ventilation
<b>Curing</b>	2% Dibenzoyl Peroxide 50 %
<b>Curing Time</b>	25 - 30 min at 23 °C
<b>Pot Life</b>	10- 15 min at 23°C
<b>Cleaning of Tools</b>	acetone, methylmethacrylate
<b>Application</b>	binder for self leveling floor coatings
<b>Storage</b>	up to 6 months when stored dry and cool

Our application technique consulting is not binding. The responsibility for the application resp. the processing of our products is in buyers hand, including property rights of third parties/patent rights. Technical data referring to our products are guide values.  
(updated December 2013)