

KUNSTSTOFF- UND FARBEN-GESELLSCHAFT mbH

An der Flurscheide 7 D-64584 Biebesheim
Tel. +49 (0) 6258-8006-0 Fax +49 (0) 6258-8006-70
E-Mail: info@kfg-biebesheim.de Internet: www.kfg-biebesheim.de



Technical Data Sheet

MMA-Harz G 21

Chemical Basis:	Methylmethacrylate resin
Appearance:	low viscous, turbid liquid
Flashpoint:	+10°C (MMA, DIN 51755)
Odour:	ester-like, sweet
Viscosity after stirring:	120 ± 20 mPa·s (23°C, Brookfield, Spindle 62, 100 rpm)
Viscosity (Efflux Time):	32 ± 2 s (23°C, 4 mm cup, DIN 53211)
Boiling Point	+100 °C
Handling	Breathing protection in case of insufficient ventilation
Curing:	2 % Dibenzoyl Peroxide 50 %
Curing Time	25-30 min at 23 °C
Pot Life	8 - 14 min at 23°C
Cleaning of Tools	Acetone, Methylmethacrylate
Application	binder for primings of a.o. concrete
Storage:	up to 6 months when stored cool and dry

Our application technique consulting is not binding. The responsibility for the application resp. the processing of our products is in buyers hand, including property rights of third parties/patent rights. Technical data referring to our products are guide values.
(updated August 2015)