

KUNSTSTOFF- UND FARBEN-GESELLSCHAFT mbH

An der Flurscheide 7 D-64584 Biebesheim
Tel. +49 (0) 6258-8006-0 Fax +49 (0) 6258-8006-70
E-Mail: info@kfg-biebesheim.de Internet: www.kfg-biebesheim.de



Technical Data Sheet

Methacryl-Harz MH 1200

Chemical Basis	methylmethacrylate resin
Appearance	viscose resin
Odour	ester like
Viscosity	1200 mPa [*] s (23°C, Brookfield spindle 63, 60 rpm)
Flash Point	+9°C
Boiling Point	+100°C
Cleaning of Tools	acetone, methylmethacrylate
Application	acrylic solid surface
Package	180 kg barrel or 950 kg IBC
Storage	up to 12 months if stored dry and cool (not over 35 °C)

Our application technique consulting is not binding. The responsibility for the application resp. the processing of our products is in buyers hand, including property rights of third parties/patent rights. Technical data referring to our products are guide values.
(updated June 2016)