

KUNSTSTOFF- UND FARBEN-GESELLSCHAFT mbH

An der Flurscheide 7 D-64584 Biebesheim
Tel. +49 (0) 6258-8006-0 Fax +49 (0) 6258-8006-70
E-Mail: info@kfg-biebesheim.de Internet: www.kfg-biebesheim.de



Technical Data Sheet

Mixed Polymer L 60-35 S

Chemical basis	Mix polymer mix of methylmethacrylate, butylmethacrylate, ethylhexylacrylate and methacrylic acid
Appearance	fines
Maximum Particle Size	1.6 mm
Glass Temperature	65°C ± 5
Powder Density	600-700 g/L
Viscosity 25% in MMA	29-35 cP [25% in MMA 23°C Brookfield spindle II 100 rpm]
Decomposition	350°C
Acid Number	3–5 mg KOH
Solubility	40 min (25% in MMA at 40°C)
Physiological Risks	not known
Devolution with Fillers¹⁾	12cm ± 2
Compatible with	Plasticizers based on maleinate and phtalate
Package	20 kg sacks on pallets
Application	coatings, road marking
Storage	keep dry

Our application technique consulting is not binding. The responsibility for the application resp. the processing of our products is in buyers hand, including property rights of third parties/patent rights. Technical data referring to our products are guide values.
(updated December 2013)

¹⁾20% L60-35S (31% in MMA), 48% barium sulphate and 32% quartz.