



Technical Data Sheet

Pulverized Acrylic Glass XP 165

Chemical Basis	Polymethylmethacrylate (recyclate)
Average Molecular Weight	ca. 150.000 g/mol
Appearance	powder, clear (colourless)
Particle Size	<= 0.8 mm
Powder Density	600 - 700 g/l
Physiological Risks	not known
Density	1,1 g/cm ³
Decomposition	above 350°C
Acid Value	< 1 mg KOH
Solution Time in MMA	100 min;[20% in MMA, at 40°C]
Viscosity	165 ± 5 cP; [20% in MMA, 23°C, Rheotec spindle II 100 rpm]
Package	20 kg PE bags or big bags
Application	acrylic solid surface
Storage	PMMA absorbs moisture up to 1%, therefore store dry

Our application technique consulting is not binding. The responsibility for the application resp. the processing of our products is in buyers hand, including property rights of third parties/patent rights. Technical data referring to our products are guide values.
(updated May 2017)