## KUNSTSTOFF- UND FARBEN-GESELLSCHAFT mbH KFG

An der Flurscheide 7 Tel. +49 (0) 6258-8006-0 D-64584 Biebesheim Fax +49 (0) 6258-8006-70

E-Mail: <u>info@kfg-biebesheim.de</u> Internet: www.kfg-biebesheim.de

## **Technical Data Sheet**

## MMA-Harz V 26

**Basic materials:** Methylmethacrylate resin, lightly elastified

**Appearance:** blueish, low viscose, turbid liquid

Flashpoint:  $+ 10^{\circ}$ C (MMA, DIN 51755)

**Odour:** ester-like

**Viscosity after stirring:**  $110 \pm 20$  mPa's (23°C, Brookfield Spindle 62, 100 rpm)

**Viscosity (Efflux time):**  $30 \pm 3 \text{ s} (23^{\circ}\text{C}, 4\text{mm cup, DIN } 53211)$ 

**Barcol Hardness:** 35

**Handling** Breathing protection in case of insufficient ventilation

Curing: 1-1.5 % Dibenzoyl Peroxide 50 %

**Curing Time** 25-30 min at 23 °C

**Pot Life** 10 - 15 min at 23°C

**Impact strength:** < 25 KJ/m<sup>2</sup>

Cleaning of Tools Acetone, Methylmethacrylate

**Application** binder for lightly elastic sealings

**Storage:** up to 6 months when stored cool and dry

Our application technique consulting is not binding. The responsibility for the application rsp. the processing of our products is in buyers hand, including property rights of third parties/patent rights. Technical data referring to our products are guide values. (updated December 2013)