

KUNSTSTOFF- UND FARBEN-GESELLSCHAFT mbH

An der Flurscheide 7 D-64584 Biebesheim
Tel. +49 (0) 6258-8006-0 Fax +49 (0) 6258-8006-70
E-Mail: info@kfg-biebesheim.de Internet: www.kfg-biebesheim.de



Technical Data Sheet

Fine Beads

Chemical Basis	Polymethylacrylate (PMMA)
Average molecular weight	> 100 000 g/mol
Appearance	fine beads
Available Particel Sizes	0 - 0,1 mm
Powder Density	600 - 700 g/L
Vicat Softening Temperature	> 80°C
Decomposition	above 350°C
Physiological Risks	not known
Package	25 kg PE-bags on pallets or in octabins
Application	dust technology, leveling agent
Storage	keep dry and cool

Our application technique consulting is not binding. The responsibility for the application resp. the processing of our products is in buyers hand, including property rights of third parties/patent rights. Technical data refering to our products are guide values.
(updated June 2016)